

TP60

TEMACOAT SPA TEMADUR HB 50

The polyurethane systems TP60 are suitable for steel surfaces exposed to climate with high humidity and salinity. The primer of the systems contains aluminium, micaceous iron oxide and zinc phosphate pigments, thus forming a very tight film with anticorrosive properties. TEMADUR HB 50 polyurethane forms an easy to clean finish with good gloss and colour retention properties. The systems are suitable for application both in the field and in painting shops.

Corrosivity categories/durability according to ISO 12944	Tikkurila Coatings code	Treatment
Steel surfaces		
S1.34, S3.19, S4.13 Corrosivity categories/durability C3-H, C4-M Steelwork in urban, maritime and industrial environment.	TP60	EPPUR240/3-FeSa2½
	TEMACOAT SPA	80 µm
	TEMACOAT SPA	100 µm
	TEMADUR HB 50	<u>60 µm</u>
	DFT	240 µm
S1.37, S4.14 Corrosivity categories/durability C4-H Steelwork in urban, maritime and industrial environment.	TP60	EPPUR280/3-FeSa2½
	TEMACOAT SPA	80 µm
	TEMACOAT SPA	140 µm
	TEMADUR HB 50	<u>60 µm</u>
	DFT	280 µm
S1.40, S4.15, S5.15, S6.04, S7.04 Corrosivity categories/durability C4-H, C5-M-H, C5-I-H Steelwork in severe urban, maritime and industrial environment, where the humidity and salinity are high.	TP60	EPPUR320/4-FeSa2½
	TEMACOAT SPA	80 µm
	TEMACOAT SPA	2 x 90 µm
	TEMADUR HB 50	<u>60 µm</u>
	DFT	320 µm
Marking of paint systems: TP60-SFS EN ISO 12944-5/S7.04 (EPPUR320/4-FeSa2½)		

COLOURS

The product is tintable with TEMASPEED colorants, thus ensuring the possibility to get shades from RAL-, BS-, NCS- and other colour cards.

SUITABLE SHOP PRIMERS

TEMABLAST EV 110, epoxy shop primer.
SD ZINC 1000 HA, zinc silicate

SURFACE PREPARATION	<p>Remove firm contaminations in order to make the cleaning easier. Remove salts, grease and oil with a suitable detergent. Rinse the surfaces thoroughly with water. (ISO 12944)</p> <p>Steel surfaces: Blast clean steel surfaces to preparation grade Sa2½. (ISO 8501 - 1)</p>
APPLICATION CONDITIONS	<p>The surface must be clean and dry and the surface temperature should remain at least 3 °C/ 5 °F above the dew point. During application and drying the temperature of the air, paint and surface should be a minimum of + 10 °C/50 °F. The relative humidity should not exceed 80 %.</p>
APPLICATION	<p>The paint should be mixed thoroughly before application and then applied in an even coat on the dry and clean surface. Application with airless or conventional spray, brush or roller. Stripe coating of sharp edges, welding seams etc. should be done by brush or roller.</p>
MAINTENANCE PAINTING	<p>Maintenance Touch-up painting is sufficient for maintenance when the rust grade is Ri1 - Ri3. (ISO 4628-3) Damages caused by transport or installation may also be repaired by touch-up painting. Remove all loose paint, clean rusty areas according to system demands. On steel surfaces small areas can be grinded or wire brushed to preparation grade St2 (SFS-ISO 8501-1). Level off the edges between the old paint film and the cleaned up areas. When using blast cleaning, be sure that there are no cracks in the remaining paint film. If the entire surface has to be overcoated, abrade the old topcoat to a rough finish. Remove all dust and other cleaning residues. Apply primers and finish according to the original paint system, qualities and film thicknesses.</p> <p>Repainting When the rust grade is Ri4 or Ri5, the entire coating must be renewed. Remove the old paint film and clean the surfaces to preparation grade Sa 2½. Recoat in accordance with the original paint system.</p>
PRODUCT INFORMATION	<p>More detailed product information is available in respective data sheets.</p>

tct\otes\metalli\system\tp60\laki22.8.2001